

VC Offshore EU

Antifouling

For Racing: Ultra Smooth, Hard, High Speed Performance Antifouling



PRODUCT DESCRIPTION

VC Offshore EU is an antifouling product effective against fouling organisms; slime, aquatic plants and animals. A Hard Antifouling suitable for professional and consumer application onto vessels in fresh and salt water. Easy application with no sanding between coats. Quick drying for rapid overcoating and flexible launch times. The smooth film provides a hard scrubbable finish for increased speed and efficiency. Ideal for racing sailors and powerboats.

PRODUCT INFORMATION

| | |
|-------------------------------|--|
| Colour | YBB710-Dover White, YBB711-Red , YBB712-Blue, YBB713-Black |
| Finish | Matt |
| Specific Gravity | 1.51 average |
| Volume Solids | 36% average |
| Converter/Curing Agent | YBA779, YBA799 |
| Typical Shelf Life | 2 years |
| VOC (As Supplied) | 558.7 g/L average |
| VOC (EU Solvent) | 368.9 g/Kg average EU Solvent Emissions Directive (Council Directive 1999/13/EC) |
| Unit Size | 750mL, 2L |

DRYING/OVERCOATING INFORMATION

| | Drying | | |
|-----------|------------|-------------|-------------|
| | 5°C (41°F) | 15°C (59°F) | 23°C (73°F) |
| Immersion | 6 hrs | 3 hrs | 2 hrs |
| Touch Dry | 1 hrs | 30 mins | 20 mins |

Note: Max. Immersion Times are as follows: 5-35°C - 6 mths

| Overcoated By | Overcoating Substrate Temperature | | | | | |
|----------------|--------------------------------------|-----|-------------|-----|-------------|-----|
| | 5°C (41°F) | | 15°C (59°F) | | 23°C (73°F) | |
| | Min | Max | Min | Max | Min | Max |
| VC Offshore EU | 3 hrs | ext | 1.5 hrs | ext | 1 hrs | ext |

APPLICATION AND USE

| | |
|---------------------------------|---|
| Preparation | <p>VC OFFSHORE Wash down with fresh water.</p> <p>OTHER ANTIFOULINGS Check for sound condition.</p> <p>BARE GRP Use VC General Thinner to clean and fully degrease the surface. Lightly sand with 240 grade paper. Rinse with fresh water and allow to dry. Use VC Tar2 to prime and protect against osmosis.</p> <p>STEEL Prime with VC Tar2 to prevent corrosion.</p> <p>LEAD Prime with VC Tar2.</p> <p>WOOD Prime with Primocon.</p> |
| Hints | <p>Mixing Stir well before use. Pour the powder (stored under the plastic hat) into the can. Stir or shake thoroughly. Once mixed, the product can be used for up to 7 days, provided it is stored with the lid on and mixed thoroughly before application.</p> <p>Cleaner YTA600 VC General Thinner</p> <p>Airless Spray Pressure: 176-210 bar. Tip size: 517 to 521.</p> <p>Conventional Spray Pressure: 2-3 bar. Tip size: 1.5-1.8 mm.</p> <p>Other For Airmix spray application: Pressure: 2 bar. Tip Size: 20-113.</p> |
| Some Important Points | <p>True colour will develop after immersion.</p> <p>Take care to apply all the paint calculated even if it means applying an extra coat. It is important for performance to apply the correct thickness.</p> <p>To prevent premature failure, ensure the correct amount of paint is applied using the coverage as a guide.</p> <p>Product temperature should be minimum 5°C/41°F and maximum 35°C/95°F.</p> <p>Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F.</p> <p>Substrate temperature should be minimum 1°C above dew point and maximum 35°C.</p> |
| Compatibility/Substrates | <p>GRP, Wood, Steel/Iron, Lead. Not suitable for use over Aluminium/Alloy substrates or zinc sprayed surfaces.</p> <p>Suitable for use on GRP, wood, steel/iron and lead.</p> <p>Can be applied direct over most types of antifoulings, provided they are in sound condition, with the exception of PTFE</p> |

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2018.

VC Offshore EU

Antifouling

For Racing: Ultra Smooth, Hard, High Speed Performance Antifouling



antifouling. Consult your local International Paint representative for specific overcoating advice if you are unsure about compatibility of VC Offshore EU over your existing coating scheme.

Number of Coats

By Roller:

Apply 2 coats of 30 microns dry for 12 months (Total DFT of 60 microns)

By Spray (Professional only):

Apply 1 coat of 60 microns dry for 12 months (Total DFT of 60 microns)

In all schemes, apply an extra stripe coat in areas of high wear such as chines, rudders, sterngear and any leading edges.

Coverage

By Roller:

(Theoretical) – 12m²/L per coat

(Practical) – 10.8m²/L per coat

By Spray (Professional only):

(Theoretical) - 6m²/L per coat

(Practical) - 3.6m²/L per coat

Recommended DFT per coat

30 microns dry per coat by roller

60 microns dry per coat by spray

Recommended WFT per coat

83 microns wet per coat by roller

167 microns wet per coat by spray

Application Methods

Airless Spray (Professional only), Conventional Spray (Professional only), Roller

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of VC Offshore EU to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

VC Offshore EU should be kept in securely closed containers during transport and storage.

Safety

GENERAL:

Contains biocides. Antifouling should only be wet sanded. Never dry sand or burn-off old antifouling. Note: For health and safety reasons, spray application should be carried out by professional applicators only and health and safety guidelines should be followed. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL:

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of VC Offshore EU cannot be disposed of through the municipal waste route or dumped without permit.

Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit www.yachtpaint.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2018.